

# QUV TESTING ASTM G53

#### **TECHNOLOGY**

SUBSTRATE

LIQUID X POWDER

PRETREATED ALUMINUM

## PRODUCT CODE:

6209-10 GLOSS WHITE

# TEST SAMPLE CURE CYCLE:

AIR DRIED FOR 14 DAYS

**# HOURS TESTED** 

1000

### **QUV SOURCE AND SETTINGS**

QUV	QUV B		
ТЕМР	60 C		
IRRADIANCE	0.71 W/M2		
CYCLE	4 HR UV/ 4 HR H20		

#### CARDINAL PRODUCTS

6209-10 SOLVENT BASED 2K POLYESTER POLYURETHANE GLOSS WHITE

340HP ALIPHATIC ISOCYANTE

HP-439 EXEMPT REDUCER

	PROCESS					
CLEANING:						
SURFACE PREPARATION:						
PRETREATMENT:	CHROMATE					
PRIMER:						
TOPCOAT:	6S09-10 MIXED 3:1:1 340HP+ HP-439 1.5-2.0 MILS DFT					
				_		
	INITIAL	FINAL	% RETENTION			
GLOSS	90.8	16	18			
DELTA E		1.06		-		

#### COMMENTS

### **DISCLAIMER**

IMPORTANT: Warranty and Disclaimer – The performance characteristics of these product vary according to the product application, operating conditions, materials applied to or use. Since these factors can affect results, we strongly recommend that you make your own tests to determine your satisfaction whether the product is of acceptable quality, has not been affected by storage or transportation and is suitable for your particular purpose under your own operating conditions prior to using any product in full scale production. Seller warrants the products to be free from defects in materials and workmanship. SUCH WARRANTY IS EXCLUSIVE AND IS IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE. No representative of ours has authority to waive or change this provision, which applies to all sales of these products.